



### Technical Data Sheet

# Greenflex<sup>®</sup> MH 40

## Ethylene Vinyl Acetate Copolymer (EVA)

### DESCRIPTION

Greenflex<sup>®</sup> MH 40 is an Ethylene Vinyl Acetate copolymer resin (EVA) for injection moulding applications.

Items produced with Greenflex<sup>®</sup> MH 40 shows high elasticity and good mechanical properties.

### APPLICATIONS

Greenflex<sup>®</sup> MH 40 is recommended for the production flexible items, foamed and crosslinked sheets for shoes.

### TYPICAL PROPERTIES

Properties	Test Method	Typical value
<b>Resin properties</b>		
Melt Flow Rate <sub>190 °C / 2.16 kg</sub> (g/10 min)	ISO 1133	1.8
Vinyl acetate content (%)	Internal method	17
Melting point (°C)	Internal method	88
Brittleness point (°C)	ASTM D 746	< -80
Vicat softening point <sub>1kg</sub> (°C)	ISO 306/A	62
<b>Mechanical properties<sup>1</sup></b>		
Tensile stress at yield (MPa)	ISO 527	5.6
Flexural modulus (MPa)	ISO 178	40
Hardness Shore A	ISO 868/A	89
Hardness Shore D	ISO 868/A	36

<sup>1</sup> Values are referred to injection moulded specimens. Actual properties are typical and may vary depending upon operating conditions.

## PROCESSING CONDITIONS

Greenflex<sup>®</sup> MH 40 is easy to mould with the newest injection moulding machines. Results are excellent.

### Typical processing conditions (\*)

Temperature profile of the barrel (°C) 140 - 200

Temperature of the mould (°C) 10 - 30

(\*) Processing conditions are depending on several parameters: the shape of the part to be manufactured, the localisation of the injection point, the injection moulding machine and the cooling of the mould.

## STORAGE AND HANDLING

Greenflex<sup>®</sup> MH 40 is supplied in pellet form. This material may readily be conveyed and bulk-fed through equipment designed for conventional palletized polyethylene resin, provided the equipment is designed to prevent accumulation of the fines and dust particles that are contained in all polyethylene resins. These fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used be equipped with filters of adequate size, operated and maintained in such a manner to ensure that no leaks develop and earthed adequately. We further recommend that good housekeeping be practised throughout your facility. Before using this product, read and understand the current POLIMERI EUROPA Safety Data Sheet for this product.

## AVAILABILITY

Contact the POLIMERI EUROPA sales office nearest to you regarding availability and your specific application requirements.

## FOOD CONTACT STATUS

Greenflex<sup>®</sup> MH 40 complies with the rules and regulations of the European Union, as well as other countries, regarding the use of plastic materials in food contact applications. Certificates of compliance are available upon request.

### TECHNICAL SERVICE

POLIMERI EUROPA S.p.A.  
Piazza Boldrini, 1  
20097 San Donato Milanese, Milan - Italy  
Tel. +39 02 520.1  
Fax +39 02 520.42436

POLIMERI EUROPA SAS  
1 Route des Dunes BP 59  
F-59279 MARDYCK - France  
Tel. +33 3 28235514  
Fax +33 3 28235520

### HEADQUARTERS

POLIMERI EUROPA S.p.A.  
Piazza Boldrini, 1  
20097 San Donato Milanese, Milan - Italy  
Tel. +39 02 520.1  
Fax +39 02 520.42901

info.polyethylene@polimerieuropa.com  
www.polimerieuropa.com

IMPORTANT: The descriptions and figures contained herein are provided to customer by way of a general information for the purposes the product is intended for. These reflect POLIMERI EUROPA's knowledge at the time of publication. Since the acknowledged various product applications by customers cannot be controlled by POLIMERI EUROPA, in no circumstances may POLIMERI EUROPA be held responsible for the results obtained from the customers manufacturing processes or for the product used in combination with other substances. By the information contained herein POLIMERI EUROPA won't release any warranty and/or any legal responsibility and/or give any suggestion on the use of the product, or grant any franchise on existing patents. The end-user, transformer shall always check the specific suitability of the product for the purposes it is intended for and its compatibility with process specifications. Moreover, the buyer shall check that retention, use or marketing of our products be in compliance with health, environmental as well as work-and-consumer-related safety requirements. It is the buyer's responsibility to inform end-user. In no circumstances will POLIMERI EUROPA be held responsible should not the buyer meet the obligations and recommendations indicated herein.